



Non-Fibered Foundation Coating

Asphalt Based Coating

- Penetrates, Preserves, & Protects Foundations, & More
- Use for Coating Entire Surface Area, Above or Below Grade
- Meets ASTM D 41 Type II



Revised: 07/23

Manufacturer:

JETCOAT
472 Brehl Avenue
Columbus, Ohio
Phone: 800-394-0047
Fax: 614-279-7201
www.JETCOATinc.com

Description

A cold-applied, liquid asphalt in a solvent system ideal for waterproofing above and below grade exterior concrete, masonry walls, and foundations that are completely dry. Dries black.

Uses

Concrete Basement Foundations

Surface Preparation

Surface must be clean, dry, and free of moisture both on and beneath surface.

Application

Stir SealBest Non-Fibered Foundation Coating thoroughly. Apply a single coat over the entire surface with a brush, roller, or airless spray unit.

Drying Time

Allow material to dry and cure for 24 hours.

Clean Up

Clean tools with mineral spirits or waterless hand cleaner before material has dried.

Coverage (Approximate)

- Concrete & Masonry Surfaces: 50-65 sq. ft. per gallon

Precautions

- Do Not Heat or Thin
- Do Not Store at Temperatures Above 100 °F
- Do Not Apply Over Coal Tar Surfaces
- Do Not Apply Where Hydrostatic Pressures Could be Encountered
- Combustible. Contains Petroleum Distillate

Safety & Environmental Precautions

- Refer to Material Safety Data Sheet Before Using
- For Exterior Application Only
- Close Container When Not in Use
- Environmental Information is on the Material Safety Data Sheet
- Do Not Reuse Empty Container
- Volatile Organic Content (VOC) is 300 gm/liter max
- Use with Adequate Ventilation
- KEEP OUT OF REACH OF CHILDREN

This product does not contain any California Proposition 65 Chemicals.

Non-Fibered Foundation Coating
Asphalt Based Coating

Form No.: JC-TD63705

Packaging

Item #	Container Size	Pack	Weight
63705	4.75 Gallon Pail	1	42 lbs.
63701	.9 Gallon Pail	6	47 lbs.

* At time of manufacturing, containers are filled to maximum. However, due to the reduction in volume that occurs after cooling and settling, the actual volume may be less.

Ingredients:	Cas No.
Petroleum Asphalt	8052-42-4
Mineral Spirits	64742-88-7