



COOL KING® 10-Year Premium White Reflective Elastomeric Roof Coating

Forms a High Solids Rubber-Like Membrane

- 10-Year Protection
- Dries Bright White
- Saves Energy
- Meets Astm D 6083 Specifications
- High-Solids Formula For Maximum Durability



Revised: 08/17

Manufacturer:

JETCOAT
472 Brehl Avenue
Columbus, Ohio
Phone: 800-394-0047
Fax: 614-279-7201
www.JETCOATinc.com

Description

A 100% acrylic, highly elastomeric, titanium fortified roof coating formulated to provide a high solids rubber-like membrane. Designed for use on metal, polyurethane foam, EPDM, APP, masonry, asphalt and wood surfaces. Forms a highly reflective barrier resulting in significant energy savings. Dries bright white.

Uses

- Asphalt Roofs
- Polyurethane Foam
- Mobile Homes
- EPDM, APP, SBS
- RV's, Concrete, Wood & More

Surface Preparation

Clean Roof - Sweep off all dirt, dust, and debris. Remove rust, mildew, oil, grease, or other foreign material on the surface. Allow freshly applied asphalt roofs to cure a minimum of 4 weeks prior to applying this coating. Scrub roof with roof cleaner or bleach solution (1 part chlorine bleach and 3 parts water). Rinse thoroughly and allow to dry.

Application

EPDM ROOFS: When coating EPDM roofs it is extremely important to remove all dust, dirt, and embedded clay to assure proper adhesion. Thoroughly scrub roof surface with roof cleaner or bleach solution (1 part chlorine bleach and 3 parts water) and pressure wash entire roof surface. Use

a wide tip on pressure washer to prevent tearing roof material. Allow surface to dry.

APPLYING ROOF COATING: Stir pail thoroughly. Do not dilute. For best results apply White Elastomeric Roof Coating with a soft brush, 3/4" nap paint roller, or high pressure sprayer (Tip Size: .021 to .025). For optimum performance, durability and warranty purposes, apply a second coat.

NOTE: This product is not recommended for gravel, dead level (flat), or shingled roof surfaces.

Drying Time

Dries to the touch in 2-3 hours. Allow 6-8 hours before applying a second coat.

Clean Up

Wash tools with water before material dries.

Weather Conditions

- Application temperature must be a minimum of 60 °F and rising. Do not apply when temperature is expected to drop below 60 °F within a 24 hour period.
- In areas where dew or fog accumulates in the early evening, it is best to coat in the morning. Stop coating by early afternoon (3:00 pm) to prevent wash off, which will occur if dew, fog, or rain arrives before coating dries.
- Do not apply if rain is imminent or forecast within 24 hours of application.

Coverage (Approximate)

- One 4.75-gallon pail will coat approximately 250-350 square feet of roof surface per coat. Two coats are recommended.

Precautions

- Do Not Thin
- Do Not Freeze
- Do Not Store At Temperatures Below 50 °F

Cool King® 10-Year Premium White Reflective Elastomeric Roof Coating
Forms a High-Solids Rubber-Like Membrane

Form No.: JC-TD66215

Safety & Environmental Precautions

- Refer to Material Safety Data Sheet Before Using
- For Exterior Application Only
- Close Container When Not in Use
- Environmental Information is on the Material Safety Data Sheet
- Do Not Reuse Empty Container
- Volatile Organic Content (VOC) is 100 gm/liter max
- KEEP OUT OF REACH OF CHILDREN

CALIFORNIA PROPOSITION 65 CHEMICAL WARNING:

This product contains chemicals known to the state of California to cause cancer and birth or developmental defects.

Packaging

Item #	Container Size	Pack	Weight
66215	4.75 Gallon Pail	1	55 lbs.
66211	.9 Gallon Pail	6	69 lbs.

* At time of manufacturing, containers are filled to maximum. However, due to the reduction in volume that occurs after cooling and settling, the actual volume may be less.

Ingredients:	Cas No.
Water	7732-18-5
100% Acrylic Emulsion Polymer	Proprietary
Limestone	16389-88-1
Titanium Dioxide	13463-67-7
Ester Alcohol	25265-77-4